



Product Name	Chemical splash resistant fabric	Reference Standard
Product Code	P-TSHM-001	
Brand/Model		
Width	150cm (+2/-1cm)	ISO 22198:2006
Gram Weight	150gsm (±5)	ISO 3801:1978
Fibre Composition	95% aramid 1313, 3% aramid 1414, 2% electrostatic yarn	
Construction Pattern		
Colour	Army Green	
Finishing	Anti-phenol chemical treatment	
Dimensional Stability	≤5%	ISO 5077:2007 After 5 *Cleaning Cycles at 40°C
Formaldehyde Content (mg/kg)	Not Detectable	ISO 14184.1:2011
pH Value	7	ISO 3701:2005
Color fastness to soaping	4-5	AATCC 61-2013
Colour Fastness to Washing	4-5	ISO 105-C06:2010
Colour Fastness to Perspiration	4-5	ISO 105-E04:2013
Colour Fastness to Rubbing	4-5 (Dry Staining)	ISO 105-X12:2016
Colour Fastness to Rubbing	4-5 (Wet Staining)	ISO 105-X12:2016
Colour Fastness to Light	4-5	ISO 105-B02:2014
Pilling Resistance	2	ISO 12945-1:2000
Flame Resistance	Compliant	EN ISO 11612:2015 A1 A2
Eletrostatic Resistance	Compliant (Half Decay Time)	EN 1149-3:2004
Waterproof performance	100 points (initial), 85-90 points after 30 washings	AATCC-22:1996
Anti-phenol performance	t>75min	EN14126:2003
Oil resistance	Level 5.5 (initial), level 4 after 30 washings	AATCC 118-2013
Breaking strength	Longitude 554N, weft 661N, conform	ASTM D5035
Tear strength	35*35	ISO13937-3
Wash Recommendations		EN ISO 6330:2013, 4N 40°C

CONTACT US AT:**SYNERTEX MATERIAL TECHNOLOGY**

Room 308, Zone 1, Building B, No. 6433, Yinggang East Road, Zhaoxiang Town, Qingpu District, Shanghai China, 201705

Phone: +86 21 6976 1398 Email: info@synertexmaterial.com

Website: www.synertexmaterial.com; www.recycledprotectivefabrics.com

All the data listed in the above table are either individual test results or the most typical indicative parameters to the best of our knowledge. Owing to existance of possible vairation or deviation from case to case, the data and information shown in the table is only fo your reference. However, Synertex Material Technology assumes no liability for the accuracy or completeness of the information.