


## SYNERTEX MATERIAL TECHNOLOGY

### TenMoSoft™



### FR&Antistatic Fabric

#### Characteristic

- Inherent FR
- Antistatic
- Easy-dye Hi Vis
- Soft-Comfortable
- More Nature
- Environment Friendly
- Much Cheaper

#### Standard:

- IEC61482- 1-2
- EN11612 A1 A2 B1 C1 F1
- EN1149-5
- GB8965.1



#### Contact us:


##### SYNERTEX MATERIAL TECHNOLOGY

Room 308, Zone 1, Building B, No. 6433, Yinggang East Road, Zhaoxiang Town,  
Qingpu District, Shanghai China, 201705

Phone: +86 21 6976 1398 Email: [info@synertexmaterial.com](mailto:info@synertexmaterial.com)

Website: [www.synertexmaterial.com](http://www.synertexmaterial.com); [www.recycledprotectivefabrics.com](http://www.recycledprotectivefabrics.com)





## PRODUCT DATA SHEET

Product Name	TenMoSoft™	Reference Standard/Test Method
Product Code	M-TSHM-001	
Width Cuttable	145cm (+2/-1cm)	ISO 22198:2006
Gram Weight	180gsm (±5)	ISO 3801:1978
Fibre Composition	Modacrylic/Lyocel/FR Fiber/Carbon	
Construction Pattern	Twill	
Colour	Yellow (Navy, Orange, Yellow, or to Customer Order)	
Dimensional Stability	≤±3%	ISO 5077:2007 After 5 * Cleaning Cycles at 40°C
Breaking Strength (N)	Warp 720; Fill 530	ISO 13934-1:2013
Tear Strength (N)	Warp 37; Fill 45	ISO 13937-2:2000
Colour Fastness to Washing	4-5	ISO 105-C06:2010
Colour Fastness to Perspiration	4-5	ISO 105-E04:2013
Colour Fastness to Rubbing (Dry)	4	ISO 105-X12:2016
Colour Fastness to Rubbing (Wet)	4	ISO 105-X12:2016
Colour Fastness to Light	4	ISO 105-B02:2014
Pilling Resistance	4	ISO 12945-1:2000
Formaldehyde Content (mg/kg)	Not Detectable	ISO 14184.1:2011
pH Value	7.3	ISO 3701:2005
Flame Resistance	Complaint	EN ISO 11612:2015 A1 A2 B1 C1 F1
Electrostatic Resistance	Complaint	EN 1149-3:2004
Arc Rating (APTV)	Pending	EN 61482-1-2:2008
Cleaning Recommendations		EN ISO 6330:2013, 4N 40°C

### Contact us:

#### SYNERTEX MATERIAL TECHNOLOGY

Room 308, Zone 1, Building B, No. 6433, Yinggang East Road, Zhaoxiang Town, Qingpu District, Shanghai China, 201705

Phone: +86 21 6976 1398 Email: [info@synertexmaterial.com](mailto:info@synertexmaterial.com)



All the data listed in the above table are either individual test results or the most typical indicative parameters to the best of our knowledge. Owing to existence of possible variation or deviation from case to case, the data and information shown in the table is only for your reference. However, Synertex Material Technology assumes no liability for the accuracy or completeness of the information.